

## **AMENDMENTS TO THE SPECIFICATION**

On page 3, prior to the paragraph 09, please delete the section title "BRIEF DESCRIPTION OF THE PREFERRED EMBODIMENT", and replace the section title with the following:

### **BRIEF DESCRIPTION OF THE DRAWINGS**

Please replace paragraph [27] on pages 6 and 7 with the following paragraph:

[27] Figs. 7A and 7B illustrate a method of preparing a flat top, typically glass table (24). A flat top table (24) is provided typically including a flat, transparent glass member. A release sheet (26), such as a sheet of fluorinated ethylene-propylene ("FEP") FEP, is laid across the table after the table is sprayed with a cleaner (38) or water. Bubbles are usually squeegeed out from between the release sheet and the table using a squeegee (40). Applicants have found that, instead of a release sheet, a 1.5 mil polyurethane sheet may be provided. This will become a "skin" to the less sticky side of the patch. That is, where the method set forth, above and below discloses lift off of the patch from the release sheet, in a preferred embodiment a 1.5 mil sheet is laid on the table and the mix has some adherence and bonding to the sheet. When the process is completed, the cured mix is lifted off with the polyurethane sheet, which becomes a "skin" to one side of the patch (typically the non-sticky side). This allows easy handling by the musician drummer – one can handle the patch by the protected "skinned" side and keep their fingers off the sticky side.